



# RAPID SET

**RAPID SET** is a specially blended copolymer emulsion containing fast drying modifiers which enhances asphalt sealers to achieve a faster drying time. **RAPID SET** has a resistance to oils, fuels and grease. Use **RAPID SET** where increased durability is needed, excellent for airport runways and taxi areas, along with all commercial and industrial properties

## Coverage

Mix well before using, add after sealer has been diluted. Use 3 to 5 gal to every 100 gal of concentrated asphalt emulsion, depending on porosity.

**Smooth to medium surfaces:** 2 gal to every 100 gal of concentrated asphalt emulsion.

**Rough to excessively rough surfaces:** 3 to 5 gal to every 100 gal of concentrated. Asphalt emulsion with 2 lbs. additional Sand 60 mesh.

## Method of Application

Add sealer into agitated machine, add water, then slowly mix in **RAPID SET** while agitating. Add any additional sand (4 lbs per gal max.) Mix well before application.

## Weather Limitations

For best results, do not apply on rainy days or when temperature is expected to drop below 45° F during the next 24 hrs. On hot days, pavement shall be pre-dampened with a fog system.

## Drying Time

4 hrs or less at 70°F, 50% humidity, depending on percentage add and application thickness.

**Color**  
Light Brown

**Clean Up**  
Water when wet,  
Bio D ® when dry.

**Packaging**  
5 gal pails  
55 gal drums

**Brewer Cote** of *Arizona*



## **Scuff Tuff**

**Scuff Tuff is the only 100% acrylic modifier on the market today for use with Brewer Cote Resurfacer II and other Asphalt-Based Sealers. Scuff Tuff is specially formulated to increase chemical resistance and film strength, along with improving color and aggregate retention. Use Scuff Tuff where increased durability is needed in high wear areas, excellent for runways and taxi areas, along with all commercial and industrial properties. Also improves resistance to oils, fuels, grease, and water.**



## Diamond Shield Fortifier

### **DSF is**

a liquid composition, active curing additive. **DSF reduces VOC's and leaves behind fresh air for all who are near your Job.** This makes jobs more desirable and valuable to customers. It makes sealer easy to broom through its enhancement of rheology modification and causes broom, squeegee marks and cut lines to seem to vanish when the film has dried. DSF works with asphalt, coal tar, blended and acrylic emulsions.

DSF functions safely and significantly to reduce the amount of time required for a surface coating to be reintroduced to vehicle traffic without damage to the film. This is because DSF works within the film to actively express water with or without the sun's help.

### **Viscosity Modification and Sand Suspension (USS)**

DSF is NOT a latex based additive and does not require water added to it before introducing to your mix design. DSF improves the flexibility of the cured film and improves bonding and film strength.

DSF's Ultimate Sand Suspension (USS) provides better sand load suspension for a longer period of time than other additives because it causes an energy that causes the sand to cling to the seal coat. As a result, contractors report no sand left in the bottom of the tank after they have sprayed out. All the sand, not just most of it, goes into the job.

DSF reduces filter and tip clogging and provides a deeper, black finish. DSF's rheology modification makes sealer smoother and silkier while lubricating pumps and equipment and allowing for easier clean up. DSF will not harm equipment or set up in the tank. Broom marks and cut lines simply seem to disappear.

### **Benefits of Active Curing**

DSF will extraordinarily increase your productivity and bottom line in the normal season while extending your season at both ends for even more profits. You can complete more jobs each month with the same number of man-hours because jobs can be completed and opened the same day without the return trip the next day. Fewer return trips, equals less fuel, labor and equipment maintenance costs per job. More time for more jobs with lower job costs equals a much higher profit margin.

Under all conditions including cooler temperatures, in shaded areas and when the sun is not present Except for excessive humidity or ground saturation, DSF will accelerate the cure time of your sealer. Because of this, DSF reduces the risk of wash out if you have your job rained on after it dries to touch. DSF also allows you to do night work because it can cure film without sun. Many Contractors are doing Night work in such places as fast food restaurants in one or two nights instead of multiple moves.

## Active Cure vs. Passive Cure

DSF works through a patented Active Cure Technology. Until DSF, seal coat could only cure through the passive curing process. This requires the sun to naturally cure a film when its heat and ultra violet rays are applied. DSF is the only patented active curing process on the market. Latex based products have no active curing property and also require the sun and the heat of the passive curing process for a seal coat film to cure when used. The process of sun and heat curing seal coat is slower because the top of the film is closest to the source and thereby cures first and creates a barrier that slows down the dry and cure time for the rest of the film below the top. That's why it is recommended to wait a minimum 24 to 48 hours before the film is reintroduced to vehicle traffic when using only the passive curing power of the sun and heat.

In contrast, DSF's Active Cure Technology creates heat and energy within the film. This heat and energy from within expel the moisture from the very bottom up and through the top. This active cure technology thereby works together with the passive curing process to give you the fastest and most consistent cured film known to man. With DSF when the film is dry to touch and no longer tacky under foot, all moisture has been expelled allowing you to reintroduce vehicle traffic in only just a few hours after the job has been completed in most cases instead of 24 to 48 hours. No other product on the market does this.

Most "set-fast" or "dry-fast" products are latex based or contain hardeners. Because latex does not have the same ability to make the sealer cure quicker, there is no comparison to DSF. Latex causes the skin over drying effect on the surface of the seal coat to happen faster which traps moisture within the seal coat. This can actually further extend the time needed for enough curing to occur to reintroduce traffic because moisture gets trapped in the film longer. Set fast products that are not primarily made of latex are hardeners. These products can make the film brittle and cause premature flaking. DSF, on the other hand, safely does the same curing work the sun does through Active Cure Technology within the film. If you put down a quality seal coat application, DSF will accelerate the cure time safely on every time making every job the quickest and best job possible.

DSF turns your sealer ultra-black every time, because the faster seal coat cures the blacker it turns. DSF virtually eliminates tracking and sand roll out. DSF reduces costs and increases profits by helping contractors get the job done the first trip. Because of this, with DSF you can increase the number of jobs completed each month with the same man-hours you have been using. This benefit of time savings to the customer along with less down time for jobs such as restaurants or hotels add up to higher value and therefore a higher bid can be justified as well. In this way, DSF pays for itself and builds the contractor a better reputation for providing fast turnaround on jobs and a greater flexibility of services to the customer. Therefore, contractors not using DSF are actually losing time and money.

### Directions:

No stirring or diluting of DSF is necessary prior to adding DSF to the sealer. Use 1/2 gallon of DSF for lower traffic to 3/4 gallon of DSF per 100 gallons of raw sealer for higher traffic. For night work, use no more than 1 1/4 gallon of DSF per 100 gallons raw seal. Open container and pour contents into your normal mixture of raw sealer cut with your normal amount of water prior to adding your sand load. Observe all seal coat manufacturer guidelines when using DSF. If sealer seams thicker than desired add a little more water until correct consistency is reached and use a little less DSF on your next mix.

**CAUTION:** Dispose of container and unused contents in accordance with Local, State, and Federal regulations. **EMPLOYERS** should obtain a copy of the Safety Data Sheet (SDS) from your supplier or directly from our website [www.diamondshieldfortifier.com](http://www.diamondshieldfortifier.com). Do not heat container or store at temperatures greater than 140° F. Do not store in direct sunlight. **DO NOT ALLOW THIS PRODUCT TO FREEZE!**

**Warning! DO NOT TAKE INTERNALLY!** Use eye protection to avoid contact with eyes. In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. Use protective measures to keep off of skin. Wash off well if product comes in contact with skin. If swallowed, **CALL PHYSICIAN IMMEDIATELY! GET MEDICAL ATTENTION. KEEP OUT OF REACH OF CHILDREN!**

**WARRANTIES:**

We, the manufacturer, warrant only that this product is free of defects since many factors which affect the results obtained from this product such as weather; workmanship, equipment utilized, and prior condition of the substrate are beyond our control. We will replace at no charge any product proved to be defective within 12 months of purchase if proof of purchase from an authorized distributor is provided. **DISCLAIMER OF The Limited Warranty is IN LIEU OF any other warranties express or implied including but not limited to any implied warranty of MERCHANTABILITY or fitness for a particular purpose; and we, the manufacturer, shall have no further liability of any kind including liability for consequential or incidental damages resulting from any defects or any delays caused by replacement or otherwise.**

**Freezability:** Do not freeze

**Shelf Life:** 1 to 2 years

**Color** Blue liquid

**Flammability:** Non-Flammable

**Container size:** 2 & 5 gal pails, 55 gal drums, 275 gal IBC totes

Distributed By

**BREWER COTE OF ARIZONA INC® THE PAVEMENT MAINTENANCE SPECIALISTS**

**5226 W. MISSOURI AVENUE, GLENDALE ARIZONA 85301**

**[www.brewercoteaz.com](http://www.brewercoteaz.com) • tel. 623-931-3728 • toll 888-931-3728 • fax 623-842-0714 • [sales@brewercoteaz.com](mailto:sales@brewercoteaz.com)**