



RESURFACER II

Resurfacer II is a milled blend of fiber reinforced asphalt, selected mineral fillers and acrylic and is polymer-modified. It is designed specially to increase the life expectancy of your asphalt.

Resurfacer II beautifies and protects both old and new parking lots, recreational areas, and driveways against moisture and water penetration, ultraviolet rays from the sun, and oxidation. The tough, durable formula fills pavement voids and low spots by replacing fines that are lost during the aging process.

ADVANTAGES

- Saves your pavement
- Increase life expectancy
- Long lasting
- Stops raveling
- Better resistance to fuel & chemicals than competitive products
- Meets all state & public works Specifications
- Can be squeegee applied to fill minor cracks & depressions
- Smooth flexible surface that is easy to clean

The Pavement Maintenance Specialists
5226 West Missouri Avenue Glendale Arizona 85301

RESURFACER II

Coverage

Smooth, dense pavements	2.0 gal. per 100 sq ft
Medium Surfaces	3.0 gal. per 100 sq ft
Rough, aged surfaces	4.5 gal. per 100 sq ft
Excessively rough surfaces	5.0 gal. per 100 sq ft

Two coats are recommended on unsealed pavements, consult project manager.

Method of Application

Make sure area is clean and free from all loose material and dirt. Squeegee or mechanical equipment product onto surface. Product may be diluted with a maximum of 20% water. Priming may be necessary on aged surfaces using one-part SS-1H and four-parts water and applied at 1 gal per 100 sq/ft. Do not over dilute Resurfacer II.

Weather Limitations

For best results, do not apply on rainy days or when the temperature is expected to drop below 50° F during the next 24 hours. On hot days, the pavement shall be pre-dampened with fog system. New asphalt should not be sealed until after exposed to a full summer heat cycle. Ambient and surface temperature must be at least 55° F and rising during application. Do not apply if rain is in the forecast for the next 24 hrs.

Drying Time

8 hrs. maximum @ 70° F
50% relative humidity.

Clean up

Water when wet,
use fuel oil when dry.

Color

Jet black finish

Packaging

5 gal pail (ship wt 54 lbs)
55 gal drums (ship wt 610 lbs)
or Bulk Transport.

Specifications

TEST	METHOD	MIN	MAX	RESULTS
Weight per gallon	ASTM D244	10.0 lbs		10.1 lbs
Cone Penetration	ASTM D217	340 mm	700 mm	370 mm
% Non-Volatile	ASMA A-1	50%	60%	57%
% Non-Volatile	ASTM D2042	20%	35%	30%
(Soluble in Trichloroethylene by wt)				
*Wet track abrasion, (Grams per sq/ft)	ASTM D3910		15.3	4.6
Percentage Loss			5%	1.5%

*Modified for Sand Seal, 8 pounds + 10 minutes



tel. 623-931-3728 • toll 888-931-3728 • fax 623-842-0714
www.brewercoteaz.com sales@brewercoteaz.com