



Brewer Cote® Inductive Cold Pour Loop Sealant

Brewer Cote® Inductive Cold Pour, Single Component Loop Sealant is a one component pourable, sand and acrylic modified asphalt emulsion for the use in sealing inductive wire loop, slots in asphalt and Portland Cement concrete. This specially formulated sealant is acrylic modified to give greater flexibility in both hot & cold climates. It also skins over quickly to form a waterproof barrier. Brewer Cote's Inductive Cold Pour Loop Sealant Meets & Exceeds Federal / State Specifications in Arizona & other States.

ADVANTAGES

- Meets all Federal, State FAA, & Military Specifications
- Resists Hydrocarbons, Gas, Oil, and Chemicals
- Spray or Squeegee application for Customized Results
- Highly Resistant to Ultra Violet Light and Water Degradation
- Tough Durable Finish that is Skid Resistant and Reduces Cleaning Costs
- Beautifies your Pavement Investment
- Eliminates Raveling and is Non-Scuffing

Brewer Cote of Arizona
The Pavement Maintenance Specialists

Brewer Cote® Inductive Cold Pour Loop Sealant

Method of Application

Ready to use. B.C. Loop Sealant can be applied by pressure feed, pump, directly from container, or by pour pot. Leave pail upside down prior to use. Mix well with mechanical mixer to make all product uniform and sand is disposed. Excess should be removed immediately by V-Squeegee to force material into loop and to avoid excess waste

Coverage

Approximately 15 ln/ft per gal. based on 1/4" wide by 2" deep slots. Coverage will vary depending on width/depth of slot and type of application method. It is not recommended for slots bigger than 5/8".

*Two coats are recommended on sealed pavements, consult project manager.

Weather Limitations

For best results, do not apply on rainy days or when the temperature is expected to drop below 45° F during the next 24 hours. Pavement slots must be free of dust, dirt and water prior to application. Use Compressed Air before applying sealant. Slot may be slightly damp to help penetration of sealant.

Drying time

Tack free in one hr. under normal conditions, 77° F , @ 50% humidity. If traffic is unavoidable, broadcast fine Dry sand over surface. Drying time will vary depending on surface temperatures. Test for traffic ability before opening.

Clean up

Water prior to Drying
Use Biodegradable PRISM®
or suitable solvent

Color

Black

Packaging

5 gal. Pails / 53 lbs.
with dissolvable liners

Specifications

<u>Test</u>	<u>Method</u>	<u>Min / Max</u>	<u>Results</u>
Viscosity Saybolt Furol	ASTM-D 244	25 -150	125.0 sec. range
Retained on No. 20 Sieve % max	ASTM-D 244 (1)	.10	.02
Particle Charge	ASTM-D 244	Positive	Positive

Specifications on Emulsion

(Crack Filling)

Pumping Stability	2	Pass	Pass
Settlement, 5 Days, % max	D 244	5.0	Pass
Residue, % max	D 244 (3)	60.0	62.0

Specifications on Residue

<u>Test</u>	<u>Method</u>	<u>Min / Max</u>	<u>Results</u>
Viscosity, 60° F. Centistokes, range	D 2170	100-9500	3.90
Maltene Distribution, Ratio, Range	D 2006-70 (4)	0.7-1.4	1.1
PC/S, Ratio, Min	D 2006-70 (4)	0.50	0.80
Asphaltenes, % max	D 2006-70	11.0	9.50

5226 West Missouri Avenue Glendale Arizona 85301
Tel 623-931-3728 Toll 888-931-3728 Fax 623-842-0714
www.brewercoteaz.com sales@brewercoteaz.com